


Product information

VITOMOUNT 125 SM-80

Double-sided self-adhesive PVC film.

Product composition



Application

VITOMOUNT 125 SM-80 was designed for versatile use. It is suitable as shatter protection film for the adhesion of car mirrors.

Product benefits

- high initial tack and high final adhesive strength
- very good aging, weathering and plasticiser resistance
- compatible with acrylic glass
- compensates slight roughnesses and thermal expansion

Technical data and product properties

peel adhesion on stainless steel acc. to DIN EN 1939:1996	at 20 °C	35 N/25 mm
shear adhesion on stainless steel acc. to DIN EN 1943:1996	at 20 °C	50 N/625 mm ²
	at 50 °C	25 N/625 mm ²
compatibility with acrylic glass	yes	
resistance against plasticiser	very good	
temperature resistance	-40 °C to 80 °C	
application temperature	15 °C to 30 °C	

Processing

The most important processing parameters and information on cleaning are listed in our Information on Processing Adhesive Tapes.

Please read the Safety Data Sheet before using or handling this product. It is not suitable for consumer goods within the meaning of the food law, not suitable for food packages and not suitable for baby products and children's toy.

Storage and shelf life

12 month after receipt of goods, when stored at 18 °C and 60 % relative humidity protected from sunlight, in original packaging.

Special Information

All data and technical information presented are based on laboratory tests or have been compiled from supplier information to the best of our knowledge. A guarantee that the values are complete and correct can however not be given. You are kindly requested to conduct your own tests to determine the suitability of our product for your applications. Our General Conditions answer any questions on guarantees and liabilities for these products insofar as no other legal regulations apply.

If you need further information about product safety, conformance, REACH or RoHS please send your e-mail to info@vito-irmen.de

06/2015 Ki