


## Product information

### VITOCOLL T 306

Thin adhesive tape based on a PET film equipped with a modified acrylate on both sides.

## Product composition



**Adhesive**, modified acrylate  
**Carrier**, PET film, 12 µm  
**Adhesive**, modified acrylate  
**Liner**, siliconised paper, yellow-brown

## Application

VITOCOLL T 306 is used for permanent adhesion to metals, varnishes as well as high and low energy surfaces.

## Product benefits

- the high coating weight allows the adhesion on rough and structured materials
- very good temperature and UV resistance

## Technical data and product properties

thickness	0.21 mm		
peel adhesion on stainless steel acc. to DIN EN 1939:1996	at 23 °C	24 N / 25 mm 30 N / 25 mm 35 N / 25 mm	after 1 min after 20 min after 24 h
shear adhesion on stainless steel acc. to DIN EN 1943:1996	at 23 °C	30 N / 625 mm <sup>2</sup>	
temperature resistance	-40 °C to 160 °C short term: up to 180 °C		
application temperature	15 °C to 30 °C		
UV resistance	very good		
resistance to chemicals With expert application resistant to most oils, grease, fuels, aliphatic solvents, weak acids, salts and alkalis.	good		

## VITOCOLL T 306

### Processing

The most important processing parameters and information on cleaning are listed in our Information on Processing Adhesive Tapes.

### Storage and shelf life

12 month after receipt of goods, when stored at 18 °C and 60 % relative humidity protected from sunlight, in original packaging

### Special Information

The data and technical information presented are characteristic or average data. All advices are given to the best of our knowledge. You are kindly requested to conduct your own tests to determine the suitability of our product for your application. Our General Conditions answer any questions on guarantees and liabilities for these products unless other legal regulations apply.

If you need further information about product safety, conformance, REACH or RoHS please send your e-mail to [info@vito-irmen.de](mailto:info@vito-irmen.de)

05/2015 Ki